

C86500

Material




Notes: Casting methods recommended for this alloy: Centrifugal, Investment, Plaster, and Sand.




Applications: Machinery parts requiring strength and toughness, lever arm, valve stems, gears.




Classified under: Manganese and leaded manganese bronze alloys. ASTM B584; formerly ASTM B147-8A


As cast values below are for sand casting. Alloy does not respond to heat treating.


Key Words: Manganese Bronze, ASTM B584; ASTM B147-8A


Physical Properties	Metric	English	Comments
Density	8.30 g/cc	0.300 lb/in ³	
Mechanical Properties	Metric	English	Comments
Hardness, Brinell	130	130	
	80	80	
	@Load 500 kg, Temperature 230 °C	@Load 1100 lb, Temperature 446 °F	
	88	88	
	@Load 500 kg, Temperature 170 °C	@Load 1100 lb, Temperature 338 °F	
	97	97	
	@Load 500 kg, Temperature -35.0 °C	@Load 1100 lb, Temperature -31.0 °F	
	98	98	
	@Load 500 kg, Temperature 20.0 °C	@Load 1100 lb, Temperature 68.0 °F	
Tensile Strength, Ultimate	490 MPa	71100 psi	
	315 MPa	45700 psi	
	@Temperature 225 °C	@Temperature 437 °F	
	370 MPa	53700 psi	
	@Temperature 175 °C	@Temperature 347 °F	
	485 MPa	70300 psi	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
	500 MPa	72500 psi	
	@Temperature -35.0 °C	@Temperature -31.0 °F	
Tensile Strength, Yield	195 MPa	28300 psi	
	175 MPa	25400 psi	
	@Strain 0.200 %, Temperature 20.0 °C	@Strain 0.200 %, Temperature 68.0 °F	
	180 MPa	26100 psi	


	@Strain 0.200 %, Temperature 175 °C	@Strain 0.200 %, Temperature 347 °F	
	180 MPa	26100 psi	
	@Strain 0.200 %, Temperature 230 °C	@Strain 0.200 %, Temperature 446 °F	
	185 MPa	26800 psi	
	@Strain 0.200 %, Temperature -40.0 °C	@Strain 0.200 %, Temperature -40.0 °F	
	195 MPa	28300 psi	
	@Strain 0.500 %, Temperature 20.0 °C	@Strain 0.500 %, Temperature 68.0 °F	
	195 MPa	28300 psi	
	@Strain 0.500 %, Temperature 175 °C	@Strain 0.500 %, Temperature 347 °F	
	195 MPa	28300 psi	
	@Strain 0.500 %, Temperature 230 °C	@Strain 0.500 %, Temperature 446 °F	
	200 MPa	29000 psi	
	@Strain 0.500 %, Temperature -40.0 °C	@Strain 0.500 %, Temperature -40.0 °F	
Elongation at Break	30 %	30 %	in 50 mm
	31 %	31 %	
	@Temperature -35.0 °C	@Temperature -31.0 °F	
	39 %	39 %	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
	54 %	54 %	
	@Temperature 225 °C	@Temperature 437 °F	
	59 %	59 %	
	@Temperature 175 °C	@Temperature 347 °F	
Reduction of Area	26 %	26 %	
	@Temperature -35.0 °C	@Temperature -31.0 °F	
	39 %	39 %	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
	62 %	62 %	
	@Temperature 225 °C	@Temperature 437 °F	
	69 %	69 %	
	@Temperature 175 °C	@Temperature 347 °F	
Creep Strength	12.0 MPa	1740 psi	for 0.1% creep in 10,000 h, at 230°C
	43.0 MPa	6240 psi	for 0.1% creep in 10,000 h, at 175°C
	190 MPa	27600 psi	for 0.1% creep in 10,000 h, at 120°C
Rupture Strength 	85.0 MPa	12300 psi	
	@Temperature 230 °C, Time 2.88e+6 sec	@Temperature 446 °F, Time 800 hour	
	250 MPa	36300 psi	
	@Temperature 230 °C, Time 32400 sec	@Temperature 446 °F, Time 9.00 hour	
	265 MPa	38400 psi	
	@Temperature 175 °C, Time 2.88e+6 sec	@Temperature 347 °F, Time 800 hour	
	300 MPa	43500 psi	
	@Temperature 175 °C, Time 1.08e+6 sec	@Temperature 347 °F, Time 300 hour	
	380 MPa	55100 psi	
	@Temperature 175 °C, Time 140000 sec	@Temperature 347 °F, Time 39.0 hour	

	420 MPa @Temperature 120 °C, Time 1.01e+6 sec	60900 psi @Temperature 248 °F, Time 280 hour	
	440 MPa @Temperature 175 °C, Time 18000 sec	63800 psi @Temperature 347 °F, Time 5.00 hour	
	500 MPa @Temperature 120 °C, Time 27000 sec	72500 psi @Temperature 248 °F, Time 7.50 hour	
Modulus of Elasticity	105 GPa	15200 ksi	
	92.0 GPa @Temperature 225 °C	13300 ksi @Temperature 437 °F	
	99.0 GPa @Temperature 170 °C	14400 ksi @Temperature 338 °F	
	101 GPa @Temperature -35.0 °C	14600 ksi @Temperature -31.0 °F	
	106 GPa @Temperature 20.0 °C	15400 ksi @Temperature 68.0 °F	
Compressive Strength	165 MPa	23900 psi	at permanent set of 0.1%
	240 MPa	34800 psi	at permanent set of 1%
	545 MPa	79000 psi	at permanent set of 10%
	150 MPa @Temperature 25.0 °C	21800 psi @Temperature 77.0 °F	0.1% set
	170 MPa @Temperature 175 °C	24700 psi @Temperature 347 °F	0.1% set
	170 MPa @Temperature -35.0 °C	24700 psi @Temperature -31.0 °F	0.1% set
	175 MPa @Temperature 230 °C	25400 psi @Temperature 446 °F	0.1% set
	205 MPa @Temperature 230 °C	29700 psi @Temperature 446 °F	1% set
	245 MPa @Temperature 25.0 °C	35500 psi @Temperature 77.0 °F	1% set
	245 MPa @Temperature 175 °C	35500 psi @Temperature 347 °F	1% set
	255 MPa @Temperature -35.0 °C	37000 psi @Temperature -31.0 °F	1% set
	400 MPa @Temperature 230 °C	58000 psi @Temperature 446 °F	10% set
	430 MPa @Temperature 175 °C	62400 psi @Temperature 347 °F	10% set
	550 MPa @Temperature 25.0 °C	79800 psi @Temperature 77.0 °F	10% set
	605 MPa @Temperature -35.0 °C	87700 psi @Temperature -31.0 °F	10% set
Fatigue Strength 	130 - 150 MPa @# of Cycles 1.00e+8	18900 - 21800 psi @# of Cycles 1.00e+8	
	145 MPa @# of Cycles 1.00e+8	21000 psi @# of Cycles 1.00e+8	
	140 - 160 MPa @# of Cycles 1.00e+7	20300 - 23200 psi @# of Cycles 1.00e+7	
	170 - 200 MPa	24700 - 29000 psi	

	@# of Cycles 1.00e+6	@# of Cycles 1.00e+6	
	240 - 265 MPa	34800 - 38400 psi	
	@# of Cycles 100000	@# of Cycles 100000	
Machinability	26 %	26 %	UNS C36000 (free-cutting brass) = 100%
Charpy Impact	42.0 J	31.0 ft-lb	
	27.0 J	19.9 ft-lb	
	@Temperature 230 °C	@Temperature 446 °F	
	33.0 J	24.3 ft-lb	
	@Temperature 175 °C	@Temperature 347 °F	
	43.0 J	31.7 ft-lb	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
	47.0 J	34.7 ft-lb	
	@Temperature -35.0 °C	@Temperature -31.0 °F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity 	0.0000840 ohm-cm @Temperature 20.0 °C	0.0000840 ohm-cm @Temperature 68.0 °F	
	0.0000841 ohm-cm @Temperature 20.0 °C	0.0000841 ohm-cm @Temperature 68.0 °F	Calculated from 20.5% IACS
	0.0000890 ohm-cm @Temperature 65.0 °C	0.0000890 ohm-cm @Temperature 149 °F	
	0.0000930 ohm-cm @Temperature 90.0 °C	0.0000930 ohm-cm @Temperature 194 °F	
	0.0000970 ohm-cm @Temperature 120 °C	0.0000970 ohm-cm @Temperature 248 °F	
	0.000102 ohm-cm @Temperature 145 °C	0.000102 ohm-cm @Temperature 293 °F	
	0.000106 ohm-cm @Temperature 175 °C	0.000106 ohm-cm @Temperature 347 °F	
	0.000109 ohm-cm @Temperature 205 °C	0.000109 ohm-cm @Temperature 401 °F	
	0.000113 ohm-cm @Temperature 235 °C	0.000113 ohm-cm @Temperature 455 °F	
Magnetic Permeability	1.09	1.09	16 kA/m field strength

Thermal Properties	Metric	English	Comments
CTE, linear 	18.0 µm/m-°C @Temperature 105 °C	10.0 µin/in-°F @Temperature 221 °F	
	18.4 µm/m-°C @Temperature 130 °C	10.2 µin/in-°F @Temperature 266 °F	
	18.8 µm/m-°C @Temperature 160 °C	10.4 µin/in-°F @Temperature 320 °F	
	19.2 µm/m-°C @Temperature 185 °C	10.7 µin/in-°F @Temperature 365 °F	
	19.6 µm/m-°C @Temperature 215 °C	10.9 µin/in-°F @Temperature 419 °F	
	20.0 µm/m-°C @Temperature 240 °C	11.1 µin/in-°F @Temperature 464 °F	
	20.3 µm/m-°C @Temperature 21.0 - 93.0 °C	11.3 µin/in-°F @Temperature 69.8 - 199 °F	

	20.4 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$ @Temperature 275 $^{\circ}\text{C}$	11.3 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$ @Temperature 527 $^{\circ}\text{F}$
Specific Heat Capacity	0.373 $\text{J}/\text{g}\cdot^{\circ}\text{C}$	0.0891 $\text{BTU}/\text{lb}\cdot^{\circ}\text{F}$
Thermal Conductivity 	87.0 $\text{W}/\text{m}\cdot\text{K}$ @Temperature 20.0 $^{\circ}\text{C}$	604 $\text{BTU}\cdot\text{in}/\text{hr}\cdot\text{ft}^2\cdot^{\circ}\text{F}$ @Temperature 68.0 $^{\circ}\text{F}$
	87.0 $\text{W}/\text{m}\cdot\text{K}$ @Temperature 20.0 $^{\circ}\text{C}$	604 $\text{BTU}\cdot\text{in}/\text{hr}\cdot\text{ft}^2\cdot^{\circ}\text{F}$ @Temperature 68.0 $^{\circ}\text{F}$
	92.0 $\text{W}/\text{m}\cdot\text{K}$ @Temperature 40.0 $^{\circ}\text{C}$	638 $\text{BTU}\cdot\text{in}/\text{hr}\cdot\text{ft}^2\cdot^{\circ}\text{F}$ @Temperature 104 $^{\circ}\text{F}$
	95.0 $\text{W}/\text{m}\cdot\text{K}$ @Temperature 70.0 $^{\circ}\text{C}$	659 $\text{BTU}\cdot\text{in}/\text{hr}\cdot\text{ft}^2\cdot^{\circ}\text{F}$ @Temperature 158 $^{\circ}\text{F}$
	98.0 $\text{W}/\text{m}\cdot\text{K}$ @Temperature 95.0 $^{\circ}\text{C}$	680 $\text{BTU}\cdot\text{in}/\text{hr}\cdot\text{ft}^2\cdot^{\circ}\text{F}$ @Temperature 203 $^{\circ}\text{F}$
	102 $\text{W}/\text{m}\cdot\text{K}$ @Temperature 125 $^{\circ}\text{C}$	708 $\text{BTU}\cdot\text{in}/\text{hr}\cdot\text{ft}^2\cdot^{\circ}\text{F}$ @Temperature 257 $^{\circ}\text{F}$
	105 $\text{W}/\text{m}\cdot\text{K}$ @Temperature 140 $^{\circ}\text{C}$	729 $\text{BTU}\cdot\text{in}/\text{hr}\cdot\text{ft}^2\cdot^{\circ}\text{F}$ @Temperature 284 $^{\circ}\text{F}$
	106 $\text{W}/\text{m}\cdot\text{K}$ @Temperature 175 $^{\circ}\text{C}$	736 $\text{BTU}\cdot\text{in}/\text{hr}\cdot\text{ft}^2\cdot^{\circ}\text{F}$ @Temperature 347 $^{\circ}\text{F}$
	109 $\text{W}/\text{m}\cdot\text{K}$ @Temperature 210 $^{\circ}\text{C}$	756 $\text{BTU}\cdot\text{in}/\text{hr}\cdot\text{ft}^2\cdot^{\circ}\text{F}$ @Temperature 410 $^{\circ}\text{F}$
	112 $\text{W}/\text{m}\cdot\text{K}$ @Temperature 235 $^{\circ}\text{C}$	777 $\text{BTU}\cdot\text{in}/\text{hr}\cdot\text{ft}^2\cdot^{\circ}\text{F}$ @Temperature 455 $^{\circ}\text{F}$
Melting Point	862 - 880 $^{\circ}\text{C}$	1580 - 1620 $^{\circ}\text{F}$
Solidus	862 $^{\circ}\text{C}$	1580 $^{\circ}\text{F}$
Liquidus	880 $^{\circ}\text{C}$	1620 $^{\circ}\text{F}$

Processing Properties	Metric	English	Comments
Annealing Temperature	260 $^{\circ}\text{C}$	500 $^{\circ}\text{F}$	

Component Elements Properties	Metric	English	Comments
Aluminum, Al	0.50 - 1.5 %	0.50 - 1.5 %	
Copper, Cu	55 - 60 %	55 - 60 %	
Iron, Fe	0.40 - 2.0 %	0.40 - 2.0 %	
Lead, Pb	≤ 0.40 %	≤ 0.40 %	
Manganese, Mn	≤ 1.5 %	≤ 1.5 %	
Nickel, Ni	≤ 1.0 %	≤ 1.0 %	
Tin, Sn	≤ 1.0 %	≤ 1.0 %	
Zinc, Zn	39 %	39 %	